

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

An  ALION Technical Center

RIVERBANK.ALIONSCIENCE.COM

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Test Report

SPONSOR: **MCM Acoustical**
Toronto, ON, Canada

Sound Absorption
RAL™-A20-219

CONDUCTED: 2020-06-12

Page 1 of 10

ON: 3/4 in. thick 32mm Grooved wood panel over 2 in. Fiberglass (Type F-50 mounting)

TEST METHODOLOGY

Riverbank Acoustical Laboratories™ is accredited by the U.S. Department of Commerce, National Institute of Standards and Technology (NIST) under the National Voluntary Laboratory Accreditation Program (NVLAP) as an ISO 17025:2017 Laboratory (NVLAP Lab Code: 100227-0) and for this test procedure. The test reported in this document conformed explicitly with ASTM C423-17: "Standard Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method." The specimen mounting was performed according to ASTM E795-16: "Standard Practices for Mounting Test Specimens During Sound Absorption Tests." A description of the measurement procedure and room specifications are available upon request. The results presented in this report apply to the sample as received from the test sponsor.

INFORMATION PROVIDED BY SPONSOR

The test specimen was designated by the sponsor as 3/4 in. thick 32mm Grooved wood panel over 2 in. Fiberglass (Type F-50 mounting). The following nominal product information was provided by the sponsor prior to testing. The accuracy of such sponsor-provided information can affect the validity of the test results.

Product Under Test

Grooved Panel

Trade Name: 32mm Grooved Panel
Thickness: 19.05 mm (0.75 in.)
Manufacturer: MCM Acoustical

Base Layer

Material: Fiberglass
Thickness: 50.8 mm (2 in.)
Density: 96-112 kg/m³(6-7 lbs/ft³)

SPECIMEN MEASUREMENTS & TEST CONDITIONS

Through a full internal inspection performed on the test specimen, Riverbank personnel verified the following information:

Base Layer

Material: Rigid fiberglass insulation board
Dimensions: 8 @ 609.6 mm (24 in.) x 1219.2 mm (48 in.)
2 @ 304.8 mm (12 in.) x 1219.2 mm (48 in.)
Thickness: 50.8 mm (2 in.)
Overall Weight: 31.75 kg (70 lbs)
Density: 93.4 kg/m³ (5.83 lbs/ft³)



® RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2017 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT. THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

An  ALION Technical Center

RIVERBANK.ALIONSCIENCE.COM

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Test Report

MCM Acoustical
2020-06-12

RAL™-A20-219

Page 2 of 10

Grooved Panel

- Materials: Grooved wood veneer over perforated/grooved medium density fiberboard core, adhered nonwoven textile backer
- Dimensions: 6 @ 914.4 mm (36 in.) x 1219.2 mm (48 in.)
- Thickness: 17.07 mm (0.672 in.)
- Face Grooves: Trapezoidal profile, width decreases with depth
Depth @ 4 mm (0.157 in.)
Opening width at top @ 3 mm (0.118 in.)
Opening width at bottom @ 2 mm (0.079 in.)
Pitch @ 32 mm (1.26 in.)
- Core Perforations: Circular holes, diameter @ 8 mm (0.315 in.)
Rectangular pitch, rows @ 32 mm (1.26 in.) on center, columns @ 16 mm (0.63 in.) on center
Approximately 9.8 % open area
- Core Grooves: Rectangular profile, superimposed over perforation rows
Cut into bottom face of core material
Depth @ 4 mm (0.157 in.)
Width @ 4 mm (0.157 in.)
Pitch @ 32 mm (1.26 in.)
- Overall Weight: 81.65 kg (180 lbs)
- Installation: Loose laid over base layer
Grooved wood veneer exposed to sound field

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

An  ALION Technical Center

RIVERBANK.ALIONSCIENCE.COM

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Test Report

MCM Acoustical
2020-06-12

RAL™-A20-219

Page 3 of 10

Overall Specimen Properties

Size: 2.74 m (108.0 in) wide by 2.44 m (96.0 in) long
Thickness: 0.07 m (2.672 in)
Weight: 113.4 kg (250.0 lbs)
Mass per Unit Area: 16.95 kg/m² (3.47 lbs/ft²)
Calculation Area: 6.689 m² (72 ft²)

Test Environment

Room Volume: 291.98 m³
Temperature: 22.1 °C ± 0.0 °C (Requirement: ≥ 10 °C and ≤ 5 °C change)
Relative Humidity: 60.55 % ± 0.3 % (Requirement: ≥ 40 % and ≤ 5 % change)
Barometric Pressure: 99.7 kPa (Requirement not defined)

MOUNTING METHOD

Type F-50 Mounting: The test specimen was laid atop an array of 50 mm (1.969 in.) thick wooden spacers, creating an air space between the test specimen and the horizontal test surface. The numeral suffix in the mounting designation is defined as the thickness of the spacers in millimeters, rounded to the nearest integer multiple of 5. Perimeter edges were sealed with wood and metal framing.

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

An **ALION** Technical Center

RIVERBANK.ALIONSCIENCE.COM

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Test Report

MCM Acoustical
2020-06-12

RAL™-A20-219

Page 4 of 10



Figure 1 – Specimen mounted in test chamber



Figure 2 – Grooved panel layer partially installed, fiberglass base layer

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

An **ALION** Technical Center

RIVERBANK.ALIONSCIENCE.COM

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Test Report

MCM Acoustical
2020-06-12

RAL™-A20-219
Page 5 of 10




Figure 3 – Individual grooved panel, face mated to base layer

1512 S BATAVIA AVENUE
 GENEVA, IL 60134
 630-232-0104

An  ALION Technical Center

RIVERBANK.ALIONSCIENCE.COM

Test Report

FOUNDED 1918 BY
 WALLACE CLEMENT SABINE

MCM Acoustical
 2020-06-12

RAL™-A20-219

Page 6 of 10

TEST RESULTS

Specimen total absorption and absorption coefficient are tabulated at the eighteen standard frequencies. A graphic presentation of the data and additional information appear on the following pages.

1/3 Octave Center Frequency (Hz)	Total Absorption (m ²)	Total Absorption (Sabins)	Absorption Coefficient
100	4.83	51.98	0.72
** 125	5.84	62.90	0.87
160	5.41	58.28	0.81
200	5.91	63.60	0.88
** 250	6.03	64.95	0.90
315	5.60	60.30	0.84
400	5.80	62.45	0.87
** 500	5.43	58.50	0.81
630	5.14	55.37	0.77
800	4.79	51.55	0.72
** 1000	4.53	48.80	0.68
1250	4.19	45.10	0.63
1600	3.77	40.59	0.56
** 2000	3.24	34.92	0.49
2500	2.83	30.43	0.42
3150	2.44	26.23	0.36
** 4000	2.38	25.67	0.36
5000	2.49	26.81	0.37

SAA = 0.71
NRC = 0.70

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

An  ALION Technical Center

RIVERBANK.ALIONSCIENCE.COM

Test Report

FOUNDED 1918 BY
WALLACE CLEMENT SABINE


MCM Acoustical
2020-06-12

RAL™-A20-219
Page 7 of 10


TEST RESULTS (continued)

The sound absorption average (SAA) is defined in ASTM C423-17 Section 3.1.1 as the arithmetic average of the sound absorption coefficients of a material for the twelve one-third octave bands from 200 Hz through 2500 Hz, inclusive, rounded to the nearest integer multiple of 0.01.

The noise reduction coefficient (NRC) is defined from previous versions of ASTM C423 as the arithmetic average of the sound absorption coefficients at 250 Hz, 500 Hz, 1000 Hz, and 2000 Hz, rounded to the nearest integer multiple of 0.05.

Tested by 
Dean Victor
Lead Experimentalist

Report by 
Malcolm Kelly
Acoustical Test Engineer

Approved by 
Eric P. Wolfram
Laboratory Manager

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

An ALION Technical Center

RIVERBANK.ALIONSCIENCE.COM

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Test Report


RAL™-A20-219

Page 8 of 10

MCM Acoustical
2020-06-12

SOUND ABSORPTION REPORT

3/4 in. thick 32mm Grooved wood panel over 2 in. Fiberglass (Type F-50 mounting)



SAA = 0.71

NRC = 0.70

1512 S BATAVIA AVENUE
 GENEVA, IL 60134
 630-232-0104

An ALION Technical Center

RIVERBANK.ALIONSCIENCE.COM

Test Report

FOUNDED 1918 BY
 WALLACE CLEMENT SABINE

MCM Acoustical
 2020-06-12

RAL™-A20-219
 Page 9 of 10

APPENDIX A: Extended Frequency Range Data

Specimen: 3/4 in. thick 32mm Grooved wood panel over 2 in. Fiberglass (Type F-50 mounting) (See Full Report)

The following non-accredited data were obtained in accordance with ASTM C423-17, but extend beyond the defined frequency range of 100Hz to 5,000Hz. These unofficial results are representative of the RAL test environment only and intended for research & comparison purposes.

1/3 Octave Band Center Frequency (Hz)	Total Absorption (Sabins)	Absorption Coefficient
31.5	2.49	0.03
40	7.73	0.11
50	9.31	0.13
63	14.25	0.20
80	23.39	0.32
<hr/>		
100	51.98	0.72
125	62.90	0.87
160	58.28	0.81
200	63.60	0.88
250	64.95	0.90
315	60.30	0.84
400	62.45	0.87
500	58.50	0.81
630	55.37	0.77
800	51.55	0.72
1000	48.80	0.68
1250	45.10	0.63
1600	40.59	0.56
2000	34.92	0.49
2500	30.43	0.42
3150	26.23	0.36
4000	25.67	0.36
5000	26.81	0.37
<hr/>		
6300	30.24	0.42
8000	28.61	0.40
10000	19.96	0.28
12500	15.67	0.22

1512 S BATAVIA AVENUE
 GENEVA, IL 60134
 630-232-0104

An  ALION Technical Center

RIVERBANK.ALIONSCIENCE.COM

Test Report

FOUNDED 1918 BY
 WALLACE CLEMENT SABINE

MCM Acoustical
 2020-06-12

RAL™-A20-219
 Page 10 of 10

APPENDIX B: Instruments of Traceability

Specimen: 3/4 in. thick 32mm Grooved wood panel over 2 in. Fiberglass (Type F-50 mounting) (See Full Report)

<u>Description</u>	<u>Model</u>	<u>Serial Number</u>	<u>Date of Certification</u>	<u>Calibration Due</u>
System 1	Type 3160-A-042	3160-106968	2019-06-25	2020-06-25
Bruel & Kjaer Mic And Preamp A	Type 4943-B-001	2311428	2019-09-27	2020-09-27
Bruel & Kjaer Pistonphone	Type 4228	2781248	2019-08-09	2020-08-09
Omega Digital Temp., Humid. And Pressure Recorder	OM-CP-PRHTemp2000	P97844	2020-02-18	2021-02-18

APPENDIX C: Revisions to Original Test Report

Specimen: 3/4 in. thick 32mm Grooved wood panel over 2 in. Fiberglass (Type F-50 mounting) (See Full Report)

<u>Date</u>	<u>Revision</u>
2020-06-12	Original report issued
2020-07-30	Page 1, Information Provided By Sponsor: Panel nominal thickness, base layer nominal thickness, and base layer nominal density were added. Pages 1, 8-10: The nominal panel thickness was added to the specimen designation. Page 2, Grooved Panel: Open area ratio estimates for perforation patterns were removed. Pages 1-10: The adjective “slotted” was replaced with the synonym “grooved”.
2022-02-17	All pages: Sponsor’s name changed to accommodate their revised corporate branding. -MP

END